

Bigfoot Enamel Paving Paint



FEATURES

Bigfoot Enamel Paving Paint is a premium quality solvent based enamel floor coating.

Formulated using a select blend of durable Alkyd resins, **Bigfoot Enamel Paving Paint** is designed to give maximum durability and weather resistance.

Bigfoot Enamel Paving Paint also exhibits excellent resistance to oil, grease, and most household chemicals making it the ideal floor coating for garages, kitchens, bathrooms and similar service areas.

RECOMMENDED USES

Bigfoot Enamel Paving Paint is suitable for a coating a variety of surfaces, including:

- Concrete walkways.
- Driveways and paths.
- Garage floors.
- General interior and exterior concrete flooring.

Bigfoot Enamel Paving Paint is suitable for both interior and exterior applications

Non-slip properties can easily be achieved by the addition of silica sand.

SPECIFICATION DATA

Generic Type:	Alkyd Enamel.	Volume Solids:	~ 41%.
Finish:	Gloss.	Dry Film Thickness:	40 – 50µ DFT
Colour:	⁽¹⁾ Available in the standard Cameleon colour range.	Wet Film Thickness:	100 - 125µ WFT
Density:	~1.01 g/cc	Coverage:	⁽²⁾ 12 - 14 m ² / litre
Packaging:	4 litre.	Number of coats:	2 - 3 depending on substrate.
Application:	Brush, roller or spray.	Touch Dry:	1 – 2 hours.
Thinner:	Mineral Turps	Dry to Recoat:	8 hours.
Cleanup:	Mineral Turps.	Hard Dry:	4 hours.
Storage:	Store under cool dry conditions away from heat and sources of ignition.		

⁽¹⁾Standard colour range of Red, Green, Black, Charcoal, Light Grey, Brown, and other colours upon request.

⁽²⁾Coverage will vary dependant on surface porosity.

DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, wax, grease and dust. Repair and sand surface if required and clean before coating.

Pre-painted surfaces should be sanded and cleaned prior to coating.

Apply the first coat thinned 5-10% with Mineral Turps to aid sealing the substrate. Apply subsequent coats un-thinned.

A non-skid effect may be achieved by sprinkling silica sand over the primary coat before drying has occurred. Allow to dry, sweep off the excess silica sand, and apply a further coat of **Bigfoot Enamel Paving Paint** to encase the non-skid particles.

Stir well and ensure colour is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with Mineral Turps.

DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.

Typical Specifications

Surface	Preparation	System	Dry Film Build
(New) Concrete surfaces	Concrete should be acid etched with a solution of hydrochloric acid in water, and allowed to dry before painting.	1. Bigfoot (thinned 5-10% with Mineral Turps) 2. Bigfoot	40 - 50µ (3)80 - 100µ
(Weathered) Concrete surfaces	Thoroughly clean the surface ensuring all traces of loose material and surface contamination (oil, grease etc) are removed.	1. Bigfoot (thinned 5-10% with Mineral Turps) 2. Bigfoot	40 - 50µ (3)80 - 100µ
(New) Timber surfaces	Fill, sand, and thoroughly clean the surface prior to application.	1. Bigfoot (thinned 5-10% with Mineral Turps) 2. Bigfoot	40 - 50µ (3)80 - 100µ
(Previously Painted) Concrete and Timber	Remove any flaking or peeling paint, fill, (if required) and sand surface. Thoroughly clean the surface ensuring all traces of dust and surface contamination (oil, grease etc) are removed.	1. Bigfoot (thinned 5-10% with Mineral Turps) 2. Bigfoot	40 - 50µ (3)80 - 100µ

⁽³⁾ 2 coats at 40 - 50 µ DFT per coat recommended.

PRECAUTIONS

See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

CAMELEON PAINTS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578
email@cameleon.com.au
www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.