

# Marble

## UltraGlossEnamel



### FEATURES

**Marble** is a premium ultra gloss alkyd enamel.

Formulated to provide a tough, flexible, long lasting quality finish, **Marble** is the perfect choice for both interior and exterior finishes.

**Marble** is easily applied by brush, roller or spray, and its unique flow properties allow an ultra high gloss finish to be achieved on suitably prepared surfaces without sacrificing opacity or gloss retention.

### RECOMMENDED USES

**Marble** is the perfect choice where a hard glossy, weather resistant coating is required, and is suitable for use on properly prepared:

- Timber
- Metal
- Brick and masonry
- Fibre sheeting

### SPECIFICATION DATA

|                      |   |                            |  |
|----------------------|---|----------------------------|--|
| <b>Generic Type:</b> | Alkyd.  | <b>Volume Solids:</b>      | ~ 52%. <sup>(1)</sup>                        |
| <b>Finish:</b>       | High Gloss.                                   | <b>Dry Film Thickness:</b> | 40 – 50µ DFT                                 |
| <b>Colour:</b>       | White.<br><i>(Full Cameleon Colour Range)</i> | <b>Wet Film Thickness:</b> | 77 - 100µ WFT                                |
| <b>Density:</b>      | ~ 1.20 g/cc <sup>(1)</sup>                    | <b>Coverage:</b>           | 9 - 10 m <sup>2</sup> / litre <sup>(1)</sup> |
| <b>Packaging:</b>    | 1 and 4 litre.                                | <b>Number of coats:</b>    | 1 - 2 depending on colour.                   |
| <b>Application:</b>  | Brush, Roller and spray                       | <b>Touch Dry:</b>          | 4 - 6 hours.                                 |
| <b>Thinner:</b>      | Mineral Turps                                 | <b>Dry to Recoat:</b>      | Overnight.                                   |
| <b>Cleanup:</b>      | Mineral Turps.                                | <b>Hard Dry:</b>           | 18 - 24 hours.                               |
| <b>Storage:</b>      | Store under cool dry conditions.              |                            |  |

<sup>(1)</sup> For White, may vary depending on colour.

### DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, grease and dust. Repair and sand surface removing any loose or peeling paint. Spot prime bare surfaces prior to top coating.

Kalsomine coated surfaces should be thoroughly scrubbed and primed with Cameleon **Unibind** prior to top coating.

Apply un-thinned, but the maximum addition of 5% Mineral Turps may be added if required.

Stir well and ensure colour (if tinted) is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with mineral turps.

**DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.**

### Typical Specifications

| Surface                                 | Preparation  | System   | Dry Film Build                       |
|---|--|--|--------------------------------------|
| <b>(Pre-painted)</b><br>Timber Surfaces | Surfaces should be sanded with all loose flaking paint removed.<br>Spot Prime with Timbaprime where the timber has been exposed.                 | 1. Timbaprime (spot-prime)<br>2. Galactic<br>3. Marble               | 50µ<br>50 - 75µ<br>(2)80 - 100µ      |
| New Timber                              | Ensure that surfaces are clean, dry and dust free.   | 1. Timbaprime<br>2. Galactic<br>3. Marble                            | 50µ<br>50 - 75µ<br>(2)80 - 100µ      |
| New Masonry and fibre sheeting          |  | 1. Unibind<br>2. Galactic<br>3. Marble                               | 50µ<br>50 - 75µ<br>(2)80 - 100µ      |
| New Steel                               | Remove any rust, repair if required, then prepare the surface to SSPC-SP-1   | 1. Acritec, or Metalprime, or Quickprime<br>2. Galactic<br>3. Marble | 50µ<br>50 - 75µ<br>(2)80 - 100µ      |
| New and weathered Galvanising           | Thoroughly scrub the surface to remove any white corrosion products and surface contamination (oil, grease etc). Prepare substrate to SSPC-SP-1. | 1. Galvabond<br>2. Galactic<br>3. Marble                             | 25 - 30µ<br>50 - 75µ<br>(2)80 - 100µ |

*(2) Recommended 2 coats @ 40 - 50µ DFT per coat*

## PRECAUTIONS

**IMPORTANT.** See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

## CAMELEON PAINTS

### Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381  
26 Paramount Drive, Wangara, Western Australia 6065  
PO Box 1473, Wangara, Western Australia 6947  
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578  
[email@cameleon.com.au](mailto:email@cameleon.com.au)  
[www.cameleon.com.au](http://www.cameleon.com.au)

### Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.