

# Acritec

## Acrylic Undercoat



### FEATURES

**Acritec** is a water based 100% acrylic undercoat specifically designed for interior and exterior use on a variety of surfaces.

**Acritec** forms an extremely strong, flexible film with excellent water resistance.

It has good adhesion and hiding power enabling it to cover repair patches and jointing compounds prior to over coating with a wide selection of Cameleon finish coats.

### RECOMMENDED USES

**Acritec** is suitable for a coating a variety of surfaces, including:

- Masonry and brick
- Cement render and Gyprock
- Porous plaster surfaces

**Acritec** is designed for use as the initial coating prior to using water based acrylic finishes. It is particularly suited to being top coated with the following Cameleon finishes:

- **Cameleon Everbrite**
- **Cameleon Splendor**
- **Cameleon Cosmic**
- **Cameleon Texas**
- **Cameleon Lifetime**
- **Cameleon Modacalce**
- **Cameleon Camilaflex**

### SPECIFICATION DATA

<b>Generic Type:</b>	Acrylic.	<b>Volume Solids:</b>	~36%.
<b>Finish:</b>	Semi Gloss.	<b>Dry Film Thickness:</b>	40 – 50 $\mu$ DFT
<b>Colour:</b>	White. <i>(Can be tinted if required)</i>	<b>Wet Film Thickness:</b>	110 - 140 $\mu$ WFT
<b>Density:</b>	~1.37 g/cc	<b>Coverage:</b>	<sup>(1)</sup> 12 - 14 m <sup>2</sup> / litre
<b>Packaging:</b>	1,2,4 and 10 litre.	<b>Number of coats:</b>	1 - 2 depending on build.
<b>Application:</b>	Brush and Roller.	<b>Touch Dry:</b>	20 - 30 minutes.
<b>Thinner:</b>	Water (if required)	<b>Dry to Recoat:</b>	4 hours.
<b>Cleanup:</b>	Water.	<b>Hard Dry:</b>	8 hours.
<b>Storage:</b>	Store under cool dry conditions.		

<sup>(1)</sup>Coverage will vary dependant on surface porosity.

## DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, grease and dust. Repair and sand surface if required and clean before coating.

Pre-painted surfaces should be sanded and cleaned prior to coating.

Apply un-thinned, but the maximum addition of 5% water may be added if required.

Stir well and ensure colour (if tinted) is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with water.

***DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.***

### Typical Specifications

Surface	Preparation	System	Dry Film Build
<b>(New)</b> Masonry, brick, Cement render, Gyprock, and Porous plaster surfaces	Thoroughly clean removing any loose material, grease, oil or dust.	1. Acritec 2. Everbrite, or Splendor, or Cosmic, or Texas, or Lifetime.	40 - 50µ <sup>(2)</sup> 80 - 100µ
<b>(Previously painted)</b> Masonry, brick, Cement render, Gyprock, and Porous plaster surfaces	Fill and sand the existing substrate, then thoroughly clean, removing any loose material, grease, oil or dust.	1. Acritec 2. Everbrite, or Splendor, or Cosmic, or Texas, or Lifetime.	40 - 50µ <sup>(2)</sup> 80 - 100µ

*<sup>(2)</sup>2 coats at 40 - 50 µ DFT per coat recommended.*

## PRECAUTIONS

See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

## CAMELEON PAINTS

### Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381  
 26 Paramount Drive, Wangara, Western Australia 6065  
 PO Box 1473, Wangara, Western Australia 6947  
 Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578  
[email@cameleon.com.au](mailto:email@cameleon.com.au)  
[www.cameleon.com.au](http://www.cameleon.com.au)



#### Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.