

Camelastic Topcoat White

Elastomeric Topcoat



FEATURES

Camelastic Topcoat White is a premium quality elastomeric coating specifically designed for direct to substrate application.

Containing a unique extender system in combination with an extremely durable elastomeric polymer system, **Camelastic Topcoat White** exhibits excellent elongation properties.

Camelastic Topcoat White has outstanding adhesion to a wide variety of substrates and the cured film provides excellent strength, durability and flexibility to the coating system. Containing film biocides to eliminate fungal and algal growth, **Camelastic Topcoat White** will provide long term protection in the harshest of environments.

RECOMMENDED USES

Camelastic Topcoat White is designed to be applied to exterior surfaces to provide a protective film that can cope with the expansion and contraction that may be experienced on large roof surfaces.

- Galvanised Iron
- Aluminium
- Concrete and cement render
- Colourbond
- Timber

Camelastic Topcoat White may be applied at medium dry film build, in most circumstances up to 250 microns DFT.

SPECIFICATION DATA

Colour:	White	WFT:	640µ WFT for 250µ DFT
Density:	~ 1.21g/cc	Coverage:	2 - 3 m ² / litre @ 250µ DFT
Volume Solids:	~42%	Number of Coats:	1 - 2 coats
Weight Solids (NVM):	~55%	Touch Dry:	1 hour @ 250µ DFT at 25°C
Packaging:	20 and 200 litre	Dry to Recoat:	24 hours (if required)
Application:	Airless spray, brush or roller	Hard Dry:	8 hours @ 250µ DFT at 25°C
Cleanup:	Water		
Storage:	Store under cool dry conditions.		

PERFORMANCE

Temperature Resistance:	Excellent
Abrasion Resistance:	Good
Weatherability:	Excellent
Colour Retention:	Excellent
Water Resistance:	Excellent

DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from contamination, including fungal or algal growth.

Camelastic Topcoat White is best applied by airless spray using a minimum pump ratio of 30:1. Spray sufficient coats wet on wet to achieve the required film build. The product will easily build to 640 μ WFT.

Stir thoroughly before use - apply un-thinned, however **Camelastic Topcoat White** may be thinned 5 - 10% with water to aid application.

Application by roller should be with a textured sleeve.

Large external areas such as roofs should be high pressure water blasted to remove any residual dirt, fungal or algal growth.

Provide adequate natural ventilation during use. Wash equipment immediately after use with water.

DO NOT apply if temperature is below 10°C or if relative humidity is >85% or rain is imminent.

Typical Specifications

Surface	*Preparation	System	Dry Film Build
Plaster, masonry, brick, cement, cement render, fibre sheeting, and wood or galvanised metal.	Thoroughly clean the surface ensuring all traces of loose material and surface contamination (oil, grease etc) are removed.	1. Camelastic Topcoat	150 - 250 μ
	Remove any flaking or peeling paint, fill and sand surface (if required).	2. Camelastic Topcoat	150 - 250 μ
	<i>Prepare galvanised or steel surfaces to SSPC-SP-1</i>		

PRECAUTIONS

See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

CAMELEON PAINTS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578
email@cameleon.com.au
www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.