

# CamtectAU660

## RecoatableAcrylicUrethane



### FEATURES

**Camtect AU660** is a premium quality two component non-yellowing acrylic modified polyurethane.

Especially formulated for the harsh West Australian climate, **Camtect AU660** will provide a high gloss finish with excellent gloss retention, chemical resistance and outstanding durability.

Due to its acrylic modification, **Camtect AU660** is easily recoated, even after years of exterior exposure.

### RECOMMENDED USES

**Camtect AU660** is the perfect choice when a high gloss, long lasting chemical resistant coating is desired for cosmetic effect. It finds uses in all the following areas:

- Marine industry
- Chemical Industry
- Road and rail tankers
- General construction

### SPECIFICATION DATA

<b>Colour:</b>	White, Clear and full Cameleon colour range	<b>Mixed Volume Solids:</b>	~42% <sup>(1)</sup>
<b>Finish:</b>	High Gloss	<b>Dry Film Thickness:</b>	40 - 50µ DFT
<b>Mixed Density:</b>	~1.19 g/cc <sup>(1)</sup>	<b>Wet Film Thickness:</b>	95 - 120µ WFT <sup>(1)</sup>
<b>Packaging:</b>	4,10 and 20 litre kits	<b>Coverage:</b>	~ 10 m <sup>2</sup> / litre @ 40µ DFT
<b>Mix Ratio:</b>	4 parts base: 1 part hardener	<b>Number of Coats:</b>	2 coats optimum
<b>Application:</b>	Spray, small areas by brush.	<b>Pot Life:</b>	8 hours @ 24°C
<b>Cleanup:</b>	Thinner AU160	<b>Touch Dry:</b>	30 minutes @ 24°C
<b>Storage:</b>	Store under cool dry conditions away from heat and sources of ignition.	<b>Dry to Recoat:</b>	16 hours minimum
		<b>Hard Dry:</b>	16 hours
		<b>Full Cure:</b>	7 days

<sup>(1)</sup> Base on Camtect AU660 White Kit

### PERFORMANCE

<b>Temperature Resistance:</b>	Up to 120°C dry heat
<b>Abrasion Resistance:</b>	Excellent
<b>Weatherability:</b>	Excellent
<b>Solvent Resistance:</b>	Excellent
<b>Chemical Resistance:</b>	Very Good.

## DIRECTIONS FOR USE

Mix 4 parts by volume of **Camtect AU660** base with 1 part by volume of **Camtect AU660** hardener. Allow to stand for 10 minutes prior to application. **Camtect AU660 Winter part B** hardener is available for use during colder, winter months to aid with faster set up.

If applying by conventional spray then thinning 5-10% with **Cameleon Thinner AU160** may be added as necessary. **Cameleon Thinner AU159** and **Cameleon Thinner AU161** have been developed for use as "fast" thinner during winter and "slow" thinner during summer, respectively.

**Camtect AU660** is best applied by conventional or airless spray. Ensure that the air-lines are free from any moisture otherwise film defects may occur. If applying by roller, use a 2 pack or foam roller and thin 15-20% with AU161 Thinner.

Provide adequate natural ventilation during use. Wash equipment immediately after use with **Cameleon Thinner AU160**.

**Camtect AU660 Accelerator** is available to speed up reaction time during cold, winter months.

**DO NOT apply if temperature is below 10°C or if relative humidity is >85%.**

### Typical Specifications

Surface	*Preparation	System	Dry Film Build
Steel (Corrosive environment)	For best performance abrasive blast to AS1627.4 Class 2 ½ ; if this is impractical then prepare surface to AS1627.7	1. Campoxy ZP550	50µ
Steel		2. Campoxy EHB585	200µ
		3. Camtect AU660	40 - 50µ
		4. Camtect AU660 <sup>(2)</sup>	40 - 50µ
Stainless steel, aluminium. Zinc alum or galvanised surfaces	Thoroughly scrub the surface to remove any white corrosion products and surface contamination (oil, grease etc). Prepare substrate to SSPC-SP-1.	1. Cametch VP628	15 - 20µ
		2. Campoxy ZP550	50µ
		3. Camtect AU660	40 - 50µ
		4. Camtect AU660 <sup>(2)</sup>	40 - 50µ

<sup>(2)</sup> Second coat of Camtect AU660 optional but recommended.

## PRECAUTIONS

*\*Note: The figures quoted for pot-life and drying times may vary with local conditions - such as ambient temperature and humidity, storage conditions, and volume mixed. If the temperature is high (>25°C), the material is stored in the open, or a large volume is mixed, then the pot-life will be significantly reduced.*

**IMPORTANT!** See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

## CAMELEON PAINTS

### Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381  
26 Paramount Drive, Wangara, Western Australia 6065  
PO Box 1473, Wangara, Western Australia 6947  
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578

[email@cameleon.com.au](mailto:email@cameleon.com.au)  
[www.cameleon.com.au](http://www.cameleon.com.au)

#### Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.