

Everbrite

100%AcrylicExteriorCoating



FEATURES

Everbrite is a premium quality water-borne 100% acrylic polymer coating, formulated to provide excellent UV protection and resistance to moisture and high humidity.

With the addition of UV stabilisers and film biocides, **Everbrite** provides outstanding gloss and colour retention, and protection from algal and fungal growth.

Everbrite will also provide a strong, flexible and durable surface with excellent adhesion that is fully scrubbable.

RECOMMENDED USES

Everbrite may be used on a variety of surfaces, both interior and exterior, including:

- Plaster and Gyprock
- Timber and plasterboard
- Brick and cement render
- Fibre sheeting
- Masonry
- Metal

Everbrite is easily applied by brush, roller or spray. For optimum results apply 2 full coats of **Everbrite**.

SPECIFICATION DATA

Generic Type:	Acrylic	Volume Solids:	~ 30 - 35% (Depending on colour)
Finish:	Gloss, Satin, Low Sheen and Matt.	Dry Film Thickness:	40 - 50 μ DFT
Colour:	White and the ⁽¹⁾ standard Cameleon colour range.	Wet Film Thickness:	130 - 170 μ WFT
Density:	~1.3 g/cc	Coverage:	⁽²⁾ 12 - 14 m ² / litre
Packaging:	1,4,10 litre.	Number of coats:	2 - 3 depending on substrate.
Application:	Brush, roller or spray.	Touch Dry:	20 - 30 minutes
Thinner:	Water (if required)	Dry to Recoat:	2 hours.
Cleanup:	Water	Hard Dry:	8 hours.
Storage:	Store under cool dry conditions		

⁽¹⁾Refer to the Cameleon Paints Colour Fan Deck.
⁽²⁾Coverage will vary dependant on surface porosity.

DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, wax, grease and dust. Repair and sand surface if required and clean before coating.

Pre-painted surfaces should be sanded and cleaned prior to coating. Powdery surfaces of Kalsomine should be thoroughly scrubbed and primed with Cameleon **Unibind** prior to top-coating with **Everbrite**.

Apply the first coat thinned 5-10% with Water to aid sealing the substrate. Apply subsequent coats un-thinned.

Stir well and ensure colour is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with Water.

DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.

Typical Specifications

Surface	Preparation	System	Dry Film Build
(New) Plaster, masonry, wood, brick or fibre sheeting.	Thoroughly clean the surface ensuring all traces of loose material and surface contamination (oil, grease etc) are removed.	1. ⁽³⁾ Acritec or Unibind 2. Everbrite	40 - 50µ ⁽⁴⁾ 80 - 100µ
Powdery Surfaces (Kalsomine)	Thoroughly scrub the surface to remove any loose material and surface contamination (oil, grease etc)	1. Unibind 2. Everbrite	40 - 50µ ⁽⁴⁾ 80 - 100µ
Gyprock and cement render	Remove any flaking or peeling paint, fill and sand surface (if required).	1. Acritec 2. Everbrite	40 - 50µ ⁽⁴⁾ 80 - 100µ
Plasterglass	Thoroughly clean the surface ensuring all traces of dust and surface contamination (oil, grease etc) are removed.	1. Plastershield 2. Everbrite	40 - 50µ ⁽⁴⁾ 80 - 100µ
Galvanised metal	<i>Prepare galvanised surfaces to SSPC-SP-1</i>	1. Galvaprim WB137 2. Everbrite	40 - 50µ ⁽⁴⁾ 80 - 100µ

⁽³⁾ Only required where the substrate is abnormally porous.

⁽⁴⁾ Note: 2 coats at 40 - 50 µ DFT per coat recommended.

PRECAUTIONS

See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

CAMELEON PAINTS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578
email@cameleon.com.au
www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.