

Modacalce

UltraflatLimeStyleAcrylic



FEATURES

Modacalce is a premium quality water borne acrylic which provides an ultra flat, finely textured finish.

Modacalce has been specifically formulated to provide the appearance of a Mediterranean wash, with the durability to withstand the harsh Australian environment.

With UV protection resin technology combined with built in water repellence, **Modacalce** provides a long lasting durable coating with low dirt pick up and resistance to mould and fungal growth.

Modacalce is available in a wide range of colours, from whites and pastels to deep rich hues.

RECOMMENDED USES

Modacalce is the perfect choice where a ultra flat finish is desired, and is ideal for masking less than perfect or uneven surfaces, both interior and exterior.

It may be applied with suitable preparation to previously painted or textured coatings, where its own fine texture and filling properties will provide additional enhancement. **Modacalce** may also be applied to the following properly prepared surfaces:

- Masonry and concrete
- Cement render
- Galvanised iron
- Fibre sheeting
- Plaster and Gyprock

SPECIFICATION DATA

Generic Type:	Water borne Acrylic.	Volume Solids:	*43%.
Finish:	Ultra Flat, fine texture	Dry Film Thickness:	50 – 100 µ.
Colour:	White. (Full Cameleon Colour Range)	Wet Film Thickness:	120 - 240 µ.
Density:	*1.66 ± 0.04 g/cc	Coverage:	*5 - 8 m ² / litre
Packaging:	4,10 and 20 litre.	Number of coats:	1 - 2
Application:	Brush, Roller and spray	Touch Dry:	1 hour.
Thinner:	Water	Dry to Recoat:	3 - 4 hours
Cleanup:	Water.	Hard Dry:	8 hours.
		Storage:	Store under cool dry conditions.

**Note: For White, may vary depending on colour.*

DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, grease and dust. Repair and sand surface removing any loose or peeling paint. Spot prime bare surfaces prior to top coating.

Kalsomine coated surfaces should be thoroughly scrubbed and primed with Cameleon **Unibind** prior to top coating.

Tilt panel cement construction, or similar pre-cast surfaces should be high pressure water cleaned to remove surface release agents. Allow the surface to dry completely before priming with Cameleon **Acritec**.

Apply 2 coats un-thinned by brush, roller or spray. Application by roller or spray will give an even appearance. Applying a finishing coat with a criss-cross action using a wide brush can be used to accentuate the fine texture. **Modacalce** can be applied at the thickness of a normal coating, or at a higher build similar to texture coatings.

Stir well and ensure colour (if tinted) is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with water.

DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.

Typical Specifications

Surface	Preparation	System	Dry Film Build
Previously painted surfaces	Surfaces should be sanded with all loose flaking paint removed.	1. Acritec 2. Modacalce	50µ 50 - 100µ
Masonry, cement render, brick	Ensure that surfaces are clean, dry and dust free.	1. Acritec 2. Modacalce	50µ 50 - 100µ
Kalsomine coated surfaces	Thoroughly scrub the surface to remove any loose material. Ensure that the surface is clean, dry and dust free.	1. Unibind 2. Modacalce	50µ 50 - 100µ
Steel or galvanised surfaces	Thoroughly scrub the surface to remove any white corrosion products and surface contamination (oil, grease etc). Prepare substrate to SSPC-SP-1.	1. Galvabond 2. Modacalce	25 - 30µ 50 - 100µ

PRECAUTIONS

See the Cameleon Paints General Safety Data Sheet, Product label, and Material Safety Data Sheet (MSDS) for health and safety information prior to use.

CAMELEON PAINTS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578

email@cameleon.com.au

www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.